

8100 WEATHERBOND SEALER
Updated July'25


8100 Weatherbond Sealer is a latex-rich styrene acrylic water-based sealer that is specially formulated to provide the ultimate protection for the finishing coats. It has excellent hiding, which promotes a richer colour appearance. This premium exterior sealer also provides excellent protection against alkaline and efflorescence.

Product Features:

- Excellent efflorescence resistance
- Excellent alkaline resistance
- Excellent hiding and high build
- Excellent adhesion
- Promotes richer colour appearance
- Excellent water resistance
- Excellent spattering resistance
- Ultra low odour and VOC
- Excellent for new walls and repainting

** Colour Enhancer Sealer which can be tintable via CCM to provide STRONG, VIBRANT colour with EXCELLENT HIDING properties. Only available in 5L pack size.

Paint Type	Product Type	Finishing	Recommended Substrate	Pack Size
Water based	Exterior	Sheen	Masonry, brick, plastering substrate and fibre board	5 Litres, 15 Litres

Composition

Pigment	: Titanium Dioxide and Mineral Extender
Binder	: Styrene Acrylic Emulsion
Thinner	: Water

Technical Data

Drying Time	: Touch Dry : 15 minutes (Dependent on temperature and humidity)
	: Hard Dry : 1 hour (Dependent on temperature and humidity)
Recoating Time	: 2 hours minimum (Dependent on temperature and humidity)
Dry Film Thickness	: Around 30 µm per coat
No. of Coats	: 1 coat
Theoretical Coverage	: 10 – 12 m ² per litre per coat (Actual coverage is dependent on substrate condition, application method, application condition and finishing appearance)
Volume Solid	: ~ 38%
Shelf Life	: Up to 36 months in tight sealed container

Application Method

Brush / Roller	: Dilute the paint with not more than 5% of water. Preferable not dilute for best performance.
----------------	--

Recommended Coating System
Emulsion Paint

Sealer / Primer	: 8100 Weatherbond Sealer	: 1 Coat
Top Coat	: Nippon Paint Exterior Products	: 2 Coats

Tilelac Textured Coating

Sealer / Primer	: 8100 Weatherbond Sealer	: 1 Coat
Textured Coat	: Tilelac Ema Base	: 1 Coat
Top Coat	: Nippon Paint Exterior Products	: 2 Coats

Surface Preparation

Remove all loose, defective paint or powdery residues, loose chalk, dust, fungus, algae and foreign matter. Treat any areas affected by fungus growth with Fungicidal Wash Solution. Repair cracks, uneven surfaces with Nippon CrackREPAIR 1000 Compound or suitable exterior grade fillers. Smoothen the filler areas with sand paper. Surfaces to be painted must be cleaned thoroughly and dry, it must be free from dirt, grease and other foreign matters. Allow all surfaces to dry completely prior to painting. Avoid painting when the moisture content and alkalinity of the walls are still high. (Recommended painting specification requires the moisture content of the walls to be below 16% measured by protimeter and alkalinity of the walls to be below pH9.) Spot prime with 8100 Weatherbond Sealer.

Cleaning

Clean up equipment with water immediately after use.

Tests

1. **ASTM D2486** on Wet Scrub Resistance, tested in-house
2. **ASTM D 3359** on Standard Test Methods for Measuring Adhesion by Tape Test, tested in-house
3. Alkaline and Efflorescence based on In-house test method

Safety Precautions

- Keep container tightly closed and keep out of reach children or away from food and drink.
- Ensure good ventilation during application and drying.
- When applying paint, it is advisable to wear eye protection.
- In case of contact with eye, rinse with plenty of water immediately and seek medical advice.
- Remove splashes from skin by using soap or water.
- Paint must always be stored in a cool place.
- When transporting paint, care must be taken. Always keep container in a secure upright position.
- Dispose off any paint waste in accordance with the appropriate Environment Quality Regulations.

Note

* Theoretical Coverage is based on a mathematical formula

$$\left[\frac{\text{Volume Solid \%} \times 10}{\text{Dry Film Thickness}} \right] = \text{m}^2/\text{lit}/\text{coat}$$

and does not consider LOSS FACTORS.

Variables like porosity of substrate, application method, dilution ratio, dry film thickness, opacity and so on will affect the loss factor and can vary from 30% - 50% or even more.

Disclaimer

The information contained in this document is provided to the best of Nippon Paint's knowledge, based on laboratory testing and practical experience. As our products are considered semi-finished goods, their performance may be influenced by conditions beyond Nippon Paint's control. As such, we can only guarantee the quality of the product itself. Minor variations may be introduced to comply with local regulations. Nippon Paint reserves the right to modify the information in this document without prior notice.

Users are encouraged to consult Nippon Paint for specific guidance on the suitability of this product for their intended use and application method.

In case of discrepancies between language versions, the English (United Kingdom) version shall prevail.