

Q-SHIELD EXTRA
Updated July'25


Q-Shield Extra is a premium exterior emulsion paint specially formulated with Pure Acrylic Technology to provide long-lasting protection under extreme tropical weather conditions. Its advanced formulation delivers superior dirt resistance, enhanced fungus and algae protection, and excellent UV durability, making it ideal for homes exposed to high humidity, rainfall, and pollution.

With its smooth matt finish and high coverage efficiency, Q-Shield Extra keeps exteriors looking clean and vibrant for longer—while meeting stringent quality standards such as SIRIM MS 134:2007. Designed for both beauty and performance, it ensures your home stays fresh and protected in any season.

Product Features:

- **Superior Dirt Resistance**
Effectively repels surface dust, dirt, and pollution stains—maintaining cleaner walls between washes.
- **Double Protection Against Fungus & Algae**
Advanced biocidal system offers lasting defence against biological growth, even in humid and shaded areas.
- **Tropical Weather Durability**
Built to withstand Malaysia's challenging climate—resisting cracking, peeling, and surface degradation over time.
- **UV & Colour Protection**
Tested to ASTM G154 (QUV-A) standards for long-term colour retention and fade resistance under intense UV exposure.
- **Smooth Matt Finish**
Provides a modern, elegant look with reduced surface glare for refined exterior aesthetics.
- **High Coverage**
Up to 10–12 m²/L, with approx. 38% volume solids for better paint film build and value per litre.
- **Certified Performance**
Complies with MS 134:2007 and awarded the SIRIM Eco-Label, ensuring quality, safety, and environmental responsibility.

Paint Type	Product Type	Finishing	Recommended Substrate	Pack Size
Water based	Exterior	Matt	Masonry, brick, plastering substrate and fibre board	1 Litre, 5 Litres, 15 Litres, and 18 Litres

Composition

Pigment	: Mainly Titanium Dioxide, Iron Oxide, Carbon Black and Organic Pigments and Mineral Extender
Binder	: Pure Acrylic Emulsion
Thinner	: Water

Technical Data

Drying Time	: Touch Dry : 20 minutes (Dependent on temperature and humidity) : Hard Dry : 1 hour (Dependent on temperature and humidity)
Recoating Time	: 2 hours (Dependent on temperature and humidity)
Dry Film Thickness	: Around 30 µm per coat (based on substrate condition)
No. of Coats	: 2 coats
Theoretical Coverage	: 10 – 12 m ² per litre per coat (Actual coverage is dependent on substrate condition, application method, application condition and finishing appearance)
Volume Solid	: ~ 38%

This Technical Data Sheet (TDS) replaces all earlier versions.

For details or to find your nearest Nippon Paint office, visit nipponpaint.com.my.

Shelf Life : Up to 36 months in tight sealed container

Application Method

Brush / Roller : Dilute the paint with not more than 5% of water. Preferable not dilute for best performance.

Recommended Coating System

Sealer / Primer	: 5400 Exterior Sealer / 5500 Wall Sealer / 8000 Expresskote Sealer / Acrylic 5170 Wall Sealer / Hi-Bond Wall Sealer (on powdery or skim-coated surface)	: 1 Coat
Top Coat	: Q-Shield Extra	: 2 Coats

Surface Preparation

Remove all loose, defective paint or powdery residues, loose chalk, dust, fungus, algae and foreign matter. Treat any areas affected by fungus growth with Fungicidal Wash Solution. Repair cracks, uneven surfaces with Nippon CrackREPAIR 1000 Compound or suitable exterior grade fillers. Smoothen the filler areas with sand paper. Surfaces to be painted must be cleaned thoroughly and dry, it must be free from dirt, grease and other foreign matters. Allow all surfaces to dry completely prior to painting. Avoid painting when the moisture content and alkalinity of the walls are still high. (Recommended painting specification requires the moisture content of the walls to be below 16% measured by protimeter and alkalinity of the walls to be below pH9.) Spot prime with Nippon Paint Exterior Wall Sealer.

Cleaning

Clean up equipment with water immediately after use.

Certificates

Complies to MS-SIRIM

Certified by: **SIRIM QAS**

Tests

1. **ASTM D3719** on Dirt Pick-Up Resistance by Natural Weathering, tested in-house
2. **ASTM G154** on QUV-A Colour Retention Resistance, tested in-house
3. **ASTM D2486** on Wet Scrub Resistance, tested in-house
4. **MS 134: 2007** on Specification for Latex Emulsion Paint for Exterior and Interior Use

Safety Precautions

- Keep container tightly closed and keep out of reach children or away from food and drink.
- Ensure good ventilation during application and drying.
- When applying paint, it is advisable to wear eye protection.
- In case of contact with eye, rinse with plenty of water immediately and seek medical advice.
- Remove splashes from skin by using soap or water.
- Paint must always be stored in a cool place.
- When transporting paint, care must be taken. Always keep container in a secure upright position.
- Dispose off any paint waste in accordance with the appropriate Environment Quality Regulations.

Note

* Theoretical Coverage is based on a mathematical formula

$$\left[\frac{\text{Volume Solid \%} \times 10}{\text{Dry Film Thickness}} \right] = \text{m}^2/\text{lit}/\text{coat}$$

and does not consider LOSS FACTORS.

Variables like porosity of substrate, application method, dilution ratio, dry film thickness, opacity and so on will affect the loss factor and can vary from 30% - 50% or even more.

Disclaimer

The information contained in this document is provided to the best of Nippon Paint's knowledge, based on laboratory testing and practical experience. As our products are considered semi-finished goods, their performance may be influenced by conditions beyond Nippon Paint's control. As such, we can only guarantee the quality of the product itself. Minor variations may be introduced to comply with local regulations. Nippon Paint reserves the right to modify the information in this document without prior notice.

Users are encouraged to consult Nippon Paint for specific guidance on the suitability of this product for their intended use and application method.

In case of discrepancies between language versions, the English (United Kingdom) version shall prevail.